



Exterior Mount Product Specifications

Product Code: CFEABWIV

8-mil white/black composite PVC with clear removable acrylic pressure-sensitive adhesive and a solid release liner.

Applications	Windows, glass doors or other transparent surfaces.
Composition	White/black PVC with clear pressure-sensitive adhesive coating and solid release liner.
Open Area	35% (approx.)
Vinyl Thickness (incl. adhesive)	8 mils (.008 in./203 microns), approx.
Release Liner Thickness	7 mils (.007 in./178 microns), approx.
Adhesive Thickness	1 mil (.001 in./25 microns), approx.
Perforation Diameter	.060 in. (1.5 mm)
Standard Widths/Lengths	54 & 60 in. x 100 & 1000 ft. (1.37 & 1.52 x 30.48 & 304.8 m); 54 in. x 25 ft (1.37 x 7.62 m) Custom sizes available by special order.
Dimensional Stability	Good
Minimum Application Temperature	40° F (4° C)
Service Temperature Range	0° F to 140° F (-17° C to 60° C)
Expected Lifetime Exterior	2 to 3 years. 6 months for clean removal. Adhesion may increase with time.
Water Resistance	Fair. Immersion in water not recommended. If exposed to rain, the use of an optically clear, compatible overlamine is recommended to prevent holes from filling with water.
Humidity Resistance	Fair
Solvent Resistance	Good
Storage Stability	1-year shelf life when stored at 70° F (21° C) and 50% relative humidity.
Colors Available	White on print side and black on adhesive side.
Printing	Use standard vinyl inks. Print on the white side, not on the release liner. Compatible with screen printing; inkjet printing using solvent, eco-solvent, mild solvent and UV-curable inks; thermal transfer; electrostatic transfer; and airbrushing.
Application	Apply to clean, dry glass surface. Use plain soap and water, rinse and dry glass well. Do NOT use ammonia, Windex® or other solvent-based glass cleaners prior to application. Not for use on vehicle windows because of reduced visibility.
Removal	Remove by peeling from surface. Remove adhesive residue on older installations, if necessary.